



**Stylish softshell jacket**

Wind- and water-proof 3 layer functional fabric with PU membrane (2,000 mm water column)  
Non-taped seams  
Breathable (2,000 g/m²/24h)  
Soft, casual stretch fabric  
2 side pockets with zipper  
2 inner pockets  
JN1021: lightly waisted  
Elastic drawstring with stopper at hem

Fabric:	Outer fabric (270 g/m²): 90% polyester, 10% elastane
Country of origin:	Bangladesch
Customs tariff number:	62024010

Care instructions:

Partner article:

Ladies' Softshell Jacket  
Art-Nr.: JN1021

Available colours

	S	M	L	XL	XXL	3XL
Weight in g	544 g	558 g	601 g	641 g	683 g	728 g
VPE (Pcs. per inner packaging / pcs. per outer packaging)	1/20	1/20	1/20	1/20	1/20	1/20

Measurements in cm	S	M	L	XL	XXL	3XL
1/2 chest	54,00 cm	57,00 cm	61,00 cm	65,00 cm	69,00 cm	73,00 cm
1/2 bottom width	52,00 cm	55,00 cm	59,00 cm	63,00 cm	67,00 cm	71,00 cm
front length from shoulder	69,00 cm	70,00 cm	71,00 cm	72,00 cm	74,00 cm	78,00 cm
length back from shoulder	75,00 cm	76,00 cm	77,00 cm	78,00 cm	80,00 cm	84,00 cm
sleeve length incl. shoulder	78,00 cm	80,00 cm	82,00 cm	84,00 cm	86,00 cm	89,00 cm

Available colours

azur (7451C)

navy (289C)

red (200C)

black (blackC)

off-white (off-white)

green (7481C)

orange (1575C)



**OEKO-TEX® Standard 100**

OEKO-Tex® CONFIDENCE IN TEXTILES STANDARD 100 15.0.70467 HOHENSTEIN HTTI Tested for harmful substances. [www.oeko-tex.com/standard100](http://www.oeko-tex.com/standard100)



**Softshell**

Softshell with TPU membrane consists of three layers. Due to the microporous TPU membrane as middle layer the material is water-proof, wind-proof and breathable at the same time.



**Breathable-Permeable to water vapour**

Functional textiles must have the ability to transport moisture from the skin to the fabric surface as fast as possible. Permeability shows how much steam in grams can evaporate on a surface of 1 m<sup>2</sup> within 24 hours. The higher this figure, the more breathable the textile is.



**Water column from 1.500 mm**

The ability to withstand water pressure without moisture penetrating into the material is given by the water column (mm). The minimum standard is a water column of 1,500 mm.