

## Trendy softshell jacket

Functional 3-layer-fabric with TPU membrane Wind-proof, breathable and water-proof (5,000 mm water column) Non-taped seams Inside made of micro fleece, mesh lining at the front 2 zipped side pockets, Zip in front lining for embroideries JN135: 1 vertical breast pocket with zip JN137: Slightly waisted JN135K: Fashionable, reflective piping at the front, back and on the sleeves

Fabric:

Country of origin:

r: 62024010

Customs tariff number:

Care instructions:



Partner article:

Men's Softshell Jacket Art-Nr.: JN135 Ladies' Softshell Jacket Art-Nr.: JN137

Outer fabric (330 g/m<sup>2</sup>): 95% polyester, 5% elastane

Volksrepublik China

Available colours

	М	L	XL	XXL
Weight in g	457 g	505 g	525 g	587 g
VPE	1/30	1/30	1/30	1/30
(Pcs. per inner packaging				
/ pcs. per outer packaging				

Measurements in cm	М	L	XL	XXL
Size	128,00	140,00	152,00	164,00
1/2 chest	43,00 cm	46,00 cm	49,00 cm	52,00 cm
1/2 bottom width	42,00 cm	45,00 cm	48,00 cm	51,00 cm
front length from shoulder	52,00 cm	56,00 cm	60,00 cm	64,00 cm
length back from shoulder	55,00 cm	59,00 cm	63,00 cm	69,00 cm
sleeve length	44,00 cm	49,00 cm	54,00 cm	58,00 cm

Available colours

aqua (2925C) carbon (433U) olive (5743U)



brown (476C) off-white (off-white)

### Features



OEKO-TEX® Standard 100

OEKO-Tex® CONFIDENCE IN TEXTILES STANDARD 100 15.0.70467 HOHENSTEIN HTTI Tested for harmful substances. www.oeko-tex.com/standard100

### Softshell

Softshell with TPU membrane consists of three layers. Due to the microporous TPU membrane as middle layer the material is water-proof, wind-proof and breathable at the same time.



# Breathable-Permeable to water vapour

Functional textiles must have the ability to transport moisture from the skin to the fabric surface as fast as possible. Permeability shows how much steam in grams can evaporate on a surface of 1 m2 within 24 hours. The higher this figure, the more breathable the textile is.



### Water column from 1.500 mm

The ability to withstand water pressure without moisture penetrating into the material is given by the water column (mm). The minimum standard is a water column of 1,500 mm.

Stand: 25.04.2024 - 18:47:04